




TECHNICAL DATA SHEET: WAXOLINE® BLUE 2RP FWN

Date: 20.06.2022

Full Shade	Reduction 1/20 TiO2	Structural Formula
		
Chemical Class:	Anthraquinone dye	1,4-bis(mesitylamino)anthraquinone
Colour Index:	C.I. Solvent Blue 104	

Product description	Physical data
Physical Form:	Bulk Density: 0,58 g/cm ³
Shade:	Melting Point: ~242°C

Product features	
Light fastness	7
Strength (%)	100±5
Moisture (%)	3.0 max
Insoluble in organic solvent (%)	0.5 max
Specific Gravity	1.3
Ash Content (%)	≤0.5
Loss on Drying (%)	≤1.0

Application & Storage

Mail fields of application:

Mainly be used in dyeing resin, transparent paint, aluminium-foil paper, wood, blocking materials and leather.

Recommended addition levels vary from 0,01% to 1% dependent on the colour and media required to be

Storage:

Stable at standard conditions. Is recommended a retest every 2 years.

The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained and does not necessarily indicate end product performance. Because of the variations in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user. KADION ESPECIALIDADES QUÍMICAS, S.L. shall not be liable for and the customer assumes all risk and liability of any use or handling of any material beyond KADION ESPECIALIDADES QUÍMICAS, S.L.'s direct control. The SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NO LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendation, nor as an inducement to practice any patented invention without permission of the patent owner.